

Guiding formulations for general industrial coatings (Water-based, Resin-free)

Internal reference: Formulations 3	Kronos 2160	Color Black FW 200	Raven 5000	Bayferrox Yellow 3920	Novoperm Yellow HR 70	Novoperm Red F3RK 70	Hostaperm Rosa E
Water	20.1	57.6	49.4	22.3	29.9	34.9	46.6
DELTA-DC® 3590 (41.5% active)	8.8	26.3	31.5	20.6	30.0	25.0	22.5
Preservative	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Optigel SH	1.0	--	--	1.0	--	--	--
DELTA-FC® 1525	1.0	1.0	1.0	1.0	1.0	1.0	1.0
Pigment	69.0	15.0	18.0	55.0	39.0	39.0	29.8
Total weight	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Pigment color index	PW 6	PBk 7	Pbk 7	PY 42	PY 83	PR 170	PR 122