

Guiding formulations for architectural and decorative paints (Solvent-based)

Internal reference: Formulations 4	Titanium Dioxide	Carbon Black	Iron Oxide Yellow	Iron Oxide Red	Phtalo-cyanine Blue	Phtalo-cyanine Green	Organic Red
Long-oil alkyd (72% solid)	25.00	45.00	35.00	30.00	45.00	45.00	30.00
DELTA-DC® 4207	0.72	1.98	1.80	2.70	1.53	1.62	1.62
Anti-skinning agent	0.50	0.50	0.50	0.50	0.50	0.50	0.50
Aerosil 200 (Degussa)	0.30	--	0.40	0.50	--	--	--
White spirit	13.48	24.52	12.30	6.30	24.97	27.88	37.88
Pigment	60.00	28.00	50.00	60.00	28.00	25.00	30.00
Total weight	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Pigment color index	PW 6	PBk 7	PY 42	PR 101	Pb 15	PG 7	PR 112