

## Technical Data Sheet

Last revised: **01-2019**

---

### MORDRY® Manganese 6

**MORDRY® Manganese 6** is a drier for coatings based on Manganese salt of saturated branched C8 acids in mineral spirit.

---

#### **Specifications:**

Specific gravity @ 25°C	: 0.89 – 0.93 g/cm <sup>3</sup>
Color (visual)	: Dark, brownish liquid
Metal content	: ca. 6.0%

Methods of analysis can be received upon request

---

#### **Applications and usage:**

**MORDRY® Manganese 6** is an active drier for coating systems, it is used most often in combination with Lead and/or Cobalt driers and an auxiliary drier. In baking system, Manganese soaps are most often used as a sole metal drier.

The normal use of level range for is:

**0.16-0.32% calculated on resin solids**

This dosage can be considered as a guideline. The optimum combination and concentrations will depend on the total formulation characteristics.

---

#### **Safety and Handling:**

**MORDRY® Manganese 6** should be handled in accordance with good industrial practice. Detailed information can be found in the Safety Data Sheet.

---

#### **Storage:**

**MORDRY® Manganese 6** should be stored at temperatures between 5 °C and 32 °C. Although **MORDRY® Manganese 6** will not freeze under ordinary conditions, best results can be insured if it is kept between the recommended temperatures prior to use. When kept in an original unopened container, it will keep up to 2 years from the date of manufacture. The production date is indicated on the container.

---

#### **Packaging:**

250 kg non-returnable metallic container.

---